

## **BIZON**



541-556

Weight

Width Туре

Brand





100% PES

 $310 \text{ g/m}^2 \pm 5\%$ 

142 ± 3 cm

woven fabric

(M)	Abrasion resistance PN-EN ISO 12947-2:2017-02	25 000 rubs	А	Maintenance
	Fuzzing and pilling PN-EN ISO 12945-2:2002	4	В	
<b>%</b>	Seam slippage PN-EN ISO 13936-2:2005	2   warp 2   weft	А	$\boxtimes$
	Wet rubbing PN-EN ISO 105-X12:2016-08	4-5	А	***
	Dry rubbing PN-EN ISO 105-X12:2016-08	4-5	А	
2	Cigarette test PN-EN 1021-1:2014-12		<b>✓</b>	

- of the fabric, but the process does not affect the look
- Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- ble to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- 5. Due to friction against the fabric, colourants can migrate from darker to brighter
- 6. Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- 8. It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year