BONITA





Composition	100% PES
Weight	370 g/m² ± 5%
Width	142 ± 3 cm
Туре	woven fabric
Brand	upholstery fabric

M _s	Abrasion resistance PN-EN ISO 12947-2:2017-02	60 000 rubs	А
	Fuzzing and pilling PN-EN ISO 12945-2:2002	5	Α
	Wet rubbing PN-EN ISO 105-X12:2016-08	4-5	А
	Dry rubbing PN-EN ISO 105-X12:2016-08	4-5	Α
2	Cigarette test		
	PN-EN 1021-1:2014-12		*

















- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented
- Fabric is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching $\ensuremath{\text{per}}$ 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.