## **CASABLANCA**



Composition

Weight

Width

Туре

Brand



Abrasion resistance PN-EN ISO 12947-2:2017-02



Seam slippage

PN-EN ISO 13936-2:2005



Cigarette test

PN-EN 1021-1:2014-12







PETPROOF





100% PES

310 g/m<sup>2</sup> ± 5%

142 ± 3 cm

knitted fabric

upholstery fabric

45 000 rubs

1 | warp

5 | weft

Α

Maintenance















- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning
  of the fabric, but the process does not affect the look.
- 2. Respective fabric batches may differ slightly in shade from the colours presented in the sampler
- Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- 4. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics
- 6. Long-term exposure to sunlight can cause discolouration
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.