

## CORD









Cigarette test PN-EN 1021-1:2014-12

omposition	100% PES	
Veight — — — — — — — — — — — — — — — — — — —	320 g/m² ± 5%	
Vidth	142 ± 3 cm	
ype	knitted fabric	
$rand \longrightarrow \longrightarrow \longrightarrow \longrightarrow \longrightarrow \longrightarrow$	upholstery fabric	
Abrasion resistance PN-EN ISO 12947-2:2017-02	45 000 rubs	A
Fuzzing and pilling PN-EN ISO 12945-2:2002	5	A
Seam slippage PN-EN ISO 13936-2:2005	4   warp 4   weft	В
Wet rubbing PN-EN ISO 105-X12:2016-08	5	A
Dry rubbing PN-EN ISO 105-X12:2016-08	5	A



REACH



Maintenance













- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- 2. Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- 4. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- 6. Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.