

DROP









Composition	100% PES
Weight	570 g/m² ± 5%
Width	142 ± 3 cm
Туре	woven fabric
Brand	upholstery fabric

M.	Abrasion resistance PN-EN ISO 12947-2:2017-02	>100 000 rubs	А
	Fuzzing and pilling PN-EN ISO 12945-2:2002	5	А
	Wet rubbing PN-EN ISO 105-X12:2016-08	4-5	А
	Dry rubbing PN-EN ISO 105-X12:2016-08	4-5	А
·iç:	Colour fastness to artificial light PN-EN ISO 105-B02:2014-11 metoda 2	5-6	В
	the mean of bursting strength PN-EN ISO 13938-1:2020-05	518 kPa the mean height at burst : 20 mm	В
2	Cigarette test PN-EN 1021-1:2014-12		✓

Maintenance















- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented $% \left(1\right) =\left(1\right) \left(1\right)$ in the sampler.
- **Manufacturer** is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter
- Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.