

EUREKA











PETPROOF

NON-FLAMMABLE

Composition

Weight Width

Type

Brand

100% PES

340 g/m² ± 5%

142 ± 3 cm

knitted fabric

upholstery fabric

	Abrasion resistance PN-EN ISO 12947-2:2017-02	45 000 rubs	A
	Fuzzing and pilling PN-EN ISO 12945-2:2002	4-5	A
×	Seam slippage PN-EN ISO 13936-2:2005	3 warp 4 weft	A
	Wet rubbing PN-EN ISO 105-X12:2016-08	4-5	A
	Dry rubbing PN-EN ISO 105-X12:2016-08	4-5	A
2	Cigarette test PN-EN 1021-1:2014-12		

















- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented
- Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter
- Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.