GRANADA



Composition Weight

Туре

Branc







WATER

100% PES

 $320 \text{ g/m}^2 \pm 5\%$

142 ± 3 cm

knitted fabric

upholstery fabric

		7
Y	// ₅	7

Abrasion resistance PN-EN ISO 12947-2:2017-02

Fuzzing and pilling
PN-EN ISO 12945-2:2002

Seam slippage
PN-EN ISO 13936-2:2005

Wet rubbing PN-EN ISO 105-X12:2016-08

Dry rubbing PN-EN ISO 105-X12:2016-08 25 000 rubs

4-5

3 | warp 3 | weft

4-5

4-5

Maintenance

В

Α

Α

Α

Δ















- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning
 of the fabric, but the process does not affect the look.
- 2. Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- 3. Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- 4. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- 5. Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- 6. Long-term exposure to sunlight can cause discolouration.
- 7. According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- 8. It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.