

TR/	ACY	Non-flammable		
20	011.01-211.17			
	Composition	95% PES, 5% COT		
		420 g/m² ± 5%		
Width		142 ± 3 cm		
	Туре	woven fa	abric	
	Brand Brand	upholste	ry fabric	
A.	Abrasion resistance PN-EN ISO 12947-2:2017-02	25 000 rubs	В	Maintenan
	Fuzzing and pilling PN-EN ISO 12945-2:2002	5	A	
~	Seam slippage PN-EN ISO 13936-2:2005	4 warp 3 weft	В	
	Wet rubbing	4-5	A	- **
	Dry rubbing PN-EN ISO 105-X12:2016-08	5	A	
;;;-	Colour fastness to artificial light	6	A	X

PN-EN ISO 105-B02:2014-11 method 2

Cigarette test PN-EN 1021-1:2014-12

1. The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.

- 2. Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- Fabrics is not liable for mechanical damage and such as may be attributa-ble to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- 5. Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- 6. Long-term exposure to sunlight can cause discolouration.
- 7. According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.

REACH