

KANARIA



Weight

Туре

Brand

-			
	1	3	a
15		1	7
-		4	9

Abrasion resistance

PN-EN ISO 12947-2:2017-02



Fuzzing and pilling

PN-EN ISO 12945-2:2002



PN-EN ISO 13936-2:2005



Wet rubbing

PN-EN ISO 105-X12:2016-08



PN-EN ISO 105-X12:2016-08



Colour fastness

PN-EN ISO 105-X12:2016-08



PN-EN 1021-1:2014-12













WATER REPELLENT

EASY TO CLEAN

NON-FLAMMABLE

100% olefin

230 g/m²± 5%

140 ± 2 cm

outdoor fabric

7/8

PN-EN ISO 105-B02

21 000 rubs	В	Maintenance
4-5	А	
3,6 warp 3,0 weft	А	
4-5	А	

4-5





- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning
- Respective fabric batches may differ slightly in shade from the colours presented
- Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributa-
- Bobbling and pilling are caused by the properties of the fabric and impossible
- 6. Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.



Category		I	II	III	IV
Col	lor fastness	7007 7008 7009 7011 7012 7013 7014 7015 7032	7002 7021 7022 7023 7026 7028 7029 7030	7003 7004 7018 7019 7020 7024	7005 7006 7010 7016 7017 7025 7027 7031
Color fastness to:		I	II	III	IV
Light	PN-EN ISO 105-B02	7	7	7/8	8
Weathering	PN-EN ISO 105-B04	6	6/7	7	7/8
UV	ASTM G-154 (1200 hours)	4	4	4/5	5
Washing	PN-EN ISO 105-CO6 40C	4/5	4/5	4/5	4/5
Sea water	PN-EN ISO 105-E02	4/5	4/5	4/5	4/5
Pool water	PN-EN ISO 105-E03	4/5	4/5	4/5	4/5
Rubbing	PN-EN ISO 105-X12	4/5	4/5	4/5	4/5

- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning
 of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributa-ble to the improper use and/or cleaning of the fabric.
- 4. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- 6. Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- 8. It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the properties of the fabric.