KORSYKA



Composition

Weight

\//idth

Туре

Brand



Abrasion resistance PN-EN ISO 12947-2:2017-02



Fuzzing and pilling PN-EN ISO 12945-2:2002



Seam slippage

PN-EN ISO 13936-2:2005



Wet rubbing

PN-EN ISO 105-X12:2016-08



Dry rubbing

PN-EN ISO 105-X12:2016-08



Colour fastness

to light

PN-EN ISO 105-X12:2016-08



Cigarette test

PN-EN 1021-1:2014-12













REPELLEN'

EASY TO CLEAN

NON-FLAMMABLE

ANTIBACTERIA

WEATHERPRO

100% olefin

 $350 \text{ g/m}^2 \pm 5\%$

140 ± 2 cm

woven fabric

outdoor fabric

PN-EN ISO 105-B02

27 000 rubs	В	Maintenance
5	А	
2,8 warp 3,7 weft	А	A
4-5	А	
4-5	А	
7/8	A	\otimes
		4 m

- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning
 of the fabric, but the process does not affect the look.
- 2. Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- 3. Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- 6. Long-term exposure to sunlight can cause discolouration.
- 7. According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- 8. It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.

Category		I	II	III	IV
Cold	or fastness	7114 7115 7116 7117	7118 7119 7120	7121 7122 7123 7124 7125 7126	7111 7112 7113
Color fastness to:		I	II	III	IV
Light	PN-EN ISO 105-B02	7	7	7/8	8
Weathering	PN-EN ISO 105-B04	6	6/7	7	7/8
uv	ASTM G-154 (1200 hours)	4	4	4/5	5
, Washing	PN-EN ISO 105-CO6 40C	4/5	4/5	4/5	4/5
Sea water	PN-EN ISO 105-E02	4/5	4/5	4/5	4/5
Pool water	PN-EN ISO 105-E03	4/5	4/5	4/5	4/5
Rubbing	PN-EN ISO 105-X12	4/5	4/5	4/5	4/5

- 1. The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- 4. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- 6. Long-term exposure to sunlight can cause discolouration.
- 7. According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.