## WEATHERPROOF EASY TO CLEAN ANTIBACTERIAL WATER REPELLENT NON-FLAMMABLE 7171-7189 100% olefin 460 g/m<sup>2</sup> ± 5% Width 140 ± 2 cm woven fabric Туре Abrasion resistance 50 000 rubs Δ Maintenance PN-EN ISO 12947-2:2017-02 Fuzzing and pilling 4-5 А PN-EN ISO 12945-2:2002 $\bowtie$ 2,5 | warp А PN-EN ISO 13936-2:2005 2,5 | weft Wet rubbing 4-5 А PN-EN ISO 105-X12:2016-08 Dry rubbing 4-5 А PN-EN ISO 105-X12:2016-08 Colour fastness 7/8 А PN-EN ISO 105-X12:2016-08 PN-EN ISO 105-B02 PN-EN 1021-1:2014-12

RFACH

- . The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- 3. Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- 4. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- 6. Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- 8. It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.