HAMILTON



Weight

Туре







100% PES

 $300 \text{ g/m}^2 \pm 5\%$

142 ± 3 cm

woven fabric

upholstery fabric

M.	
••••	

Abrasion resistance PN-EN ISO 12947-2:2017-02

PN-EN ISO 12945-2:2002



Seam slippage PN-EN ISO 13936-2:2005



PN-EN ISO 105-X12:2016-08



PN-EN ISO 105-X12:2016-08

30 000 rubs

3

4 | warp

3 | weft

4-5

4, 4-5

В

D

Α

Α

В

Maintenance















- 2. Respective fabric batches may differ slightly in shade from the colours presented
- Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- 4. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- 6. Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.