




# HARRIS

 7521-7526



Composition	100% olefin
Weight	416 g/m <sup>2</sup> ± 5%
Width	140 ± 2 cm
Type	woven fabric
Brand	outdoor fabric



Abrasion resistance PN-EN ISO 12947-2:2017-02	20 000 rubs	C
--	-------------	---



Fuzzing and pilling PN-EN ISO 12945-2:2002	4-5	A
---	-----	---



Seam slippage PN-EN ISO 13936-2:2005	2,4   warp 3,8   weft	A
---	--------------------------	---



Colour fastness to light PN-EN ISO 105-X12:2016-08	7/8	A
---	-----	---



Cigarette test PN-EN 1021-1:2014-12	PN-EN ISO 105-B02	✓
--	-------------------	---

## Maintenance



1. Fabrics with the Cleanaboo technology have properties that limit the absorption of liquids, are hydrophobic - not waterproof and not watertight.
2. The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
3. Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
4. Fabrics are not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
5. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
6. Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
7. Long-term exposure to sunlight can cause discolouration.
8. According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
9. It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.