

# HYGGE

 2531-2559



NON-FLAMMABLE



WATER REPELLENT



Composition	100% PES
Weight	240 g/m <sup>2</sup> ± 5%
Width	142 ± 3 cm
Type	woven fabric
Brand	upholstery fabric



Abrasion resistance

PN-EN ISO 12947-2:2017-02

100 000 rubs

A



Fuzzing and pilling

PN-EN ISO 12945-2:2002

4

B



Seam slippage

PN-EN ISO 13936-2:2005

4 | warp  
4 | weft

A



Wet rubbing

PN-EN ISO 105-X12:2016-08

4-5

A



Dry rubbing

PN-EN ISO 105-X12:2016-08

5

A



Colour fastness  
to light

4-5

c



Cigarette test

PN-EN 1021-1:2014-12

✓

Maintenance



- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.