




KENIA

 700-702, 793-799



Composition	67% olefin, 33% PES
Weight	290 g/m ² ± 5%
Width	142 ± 3 cm
Type	woven fabric
Brand	upholstery fabric

				Maintenance
	Abrasion resistance PN-EN ISO 12947-2:2017-02	25 000 rubs	B	
	Fuzzing and pilling PN-EN ISO 12945-2:2002	5	A	
	Seam slippage PN-EN ISO 13936-2:2005	4 warp 5 weft	B	     

- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- Toptextil Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.