

ROMA COLLECTION

Pelle bovina mezzo fiore stampata di spessore finito 0,8 – 1,0 mm.

Superficie media 4,8 – 5,0 m². Concia al cromo.

Tintura passante, rifinitura all'acqua con resine e pigmenti. Articolo con mano morbida, tatto ceroso ed aspetto opaco.

Bovine of Extra European origin, corrected and embossed for enhanced grain consistency.

Finished thickness is 0.8 – 1.0 mm. The average size of each hide is around 4.8 – 5.0 sqm.

Chrome tannage, through dyed, water finishing with resins and pigments.

Article with pigmented and protective top coat, and a soft, waxy feel and matt appearance.

Südamerikanisches Rindsleder mit leichter Prägung.

Stärke 0,8 – 1,0 mm. Durchschnittliche Hautgröße ca. 4,8 – 5,0 qm.

Leder mit wachsartigem, weichem Griff und seidenmatter Optik.

Vachette d'origine Extra-européenne, rectifiée et grains imprimés.

Epaisseur: 0,8 – 1,0 mm. Superficie moyenne: 4,8 – 5,0 m².

Teint dans la masse. Cet article présente sur toute la superficie une main très souple. Le touché est ciré et l'aspect opaque.

Analisi Test Analysen Essai	Metodo di prova Test Method Prüfverfahren Test Méthode	Unità di misura Measurement Unit Maßeinheit Unité de Mesure	Garantito Guaranteed Garantiert Assuré
Resistenza allo Strappo Pantalone Tear strength - Single edge tear Reißfestigkeit Hose Résistance au déchirement	UNI EN ISO 3377-1	N	> = 20
Solidità del colore allo strofinio - Secco 500 Cicli Colour fastness to rubbing - Dry 500 Cycles Abriebfestigkeit - Trocken 500 Zyklen Résistance aux frottements - A sec 500 Cycles	UNI EN ISO 11640:1998	Scala dei Grigi Grey Scale Grauskala Échelle de gris	> = 4
Solidità del colore allo strofinio - Umido 250 Cicli Colour fastness to rubbing - Wet 250 Cycles Abriebfestigkeit - Nass 250 Zyklen Résistance aux frottements - Humide 250 Cycles	UNI EN ISO 11640:1998	Scala dei Grigi Grey Scale Grauskala Échelle de gris	> = 4
Solidità del colore allo strofinio - Sudore 80 Cicli Colour fastness to rubbing - Sweat 80 Cycles Abriebfestigkeit - Schweiß 80 Zyklen Résistance aux frottements - Sueur 80 Cycles	UNI EN ISO 11640:1998 ISO 11641 pH8	Scala dei Grigi Grey Scale Grauskala Échelle de gris	> = 4
Resistenza alle flessioni - Secco 50.000 Cicli Flexing endurance - Dry 50.000 Cycles Biegefestigkeit - Trocken 50.000 Zyklen Résistance à la flexion - A sec 50.000 Cycles	UNI EN ISO 5402		Nessun danno No damage Keine Beschädigung Aucun dommage
Adesione della rifinitura - A secco Finish Adhesion - Dry Haftung der Oberflächenbehandlung - Trocken Adhésion du film - A sec	UNI EN ISO 11644	N/cm	> = 2
Solidità del colore alla luce artificiale - Energia di esposizione 16.000 kj/m ² Colour fastness to artificial light - Exposition energy 16.000 kj/sqm. UV-Beständigkeit - Expositions energie 16.000 kj/qm. Résistance à la lumière - Énergie d'exposition 16.000 kj/m ²	UNI EN ISO 105 B02 (MET.5)	Scala dei Blu Blue Scale Blauskala Échelle des bleus	> = 5
Resistenza alla sigaretta e alla piccola fiamma Burning behaviour to cigarette and match flame Brandverhalten ggü. Zigaretteglut und Streichholzflamme Comportement de combustion cigarettes et allumettes	BS 5852:1979 BS EN 1021-1-2:2006		Passa Pass Bestanden Passe

LEATHERCARE

Evitare la luce diretta del sole. Evitare l'esposizione alle fonti di calore.

Avoid direct sunlight. Avoid exposure to heat sources.

Direkte Sonneneinstrahlung vermeiden. Keinen Wärmequellen aussetzen.

Eviter la lumière directe du soleil. Eviter l'exposition à toute source de chaleur.