

## **ZORA**





213.01-213.09

PN-EN 1021-1:2014-12

100% PES Composition Weight  $380 \text{ g/m}^2 \pm 5\%$ Width 142 ± 3 cm woven fabric Туре upholstery fabric Brand

	Abrasion resistance PN-EN ISO 12947-2:2017-02	80 000 rubs	А
	Fuzzing and pilling PN-EN ISO 12945-2:2002	4	В
	Wet rubbing PN-EN ISO 105-X12:2016-08	4-5	А
	Dry rubbing PN-EN ISO 105-X12:2016-08	4-5	А
;ċ	Colour fastness to artificial light PN-EN ISO 105-B02:2014-11 method 2	6-7	А
*	Seam slippage PN-EN ISO 13936-2:2005	4   warp 5   weft	В
2	Cigarette test		./

Maintenance















- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented
- Manufacturer is not liable for mechanical damage and such as may be attributa-ble to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching  $\ensuremath{\mathsf{per}}$  10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.